

MACbond B 1280


GENERAL INTRODUCTION

MACbond

- is an assembling system consisting of a thin carrier (paper, non woven, film or others), coated on both sides with a uniform layer of adhesive.
- the adhesives used are pressure-sensitive acrylic polymer or synthetic rubber based formulations.
- is produced in roll or sheet format with a single or double release liner, so that the product chosen best suits the customer's needs.

PRODUCT DESCRIPTION

MACbond B 1280 consists of a thin polypropylene film coated on both sides with a rubber based adhesive. It offers very high tack and peel and a good cohesion.



MACbond B 1280 is produced in self-wound format on a paper liner.

TYPICAL APPLICATION

For general applications where high initial adhesion is required.
White Goods Industry: Gasket and seal mounting, mounting of nameplates, emblems and backprinted graphics.

CHARACTERISTICS

Adhesion with Substrates

| | | | |
|--------------------------|------|-------------------------|------|
| Metal / Aluminium | High | Textile/Cotton | High |
| Glass / Ceramics | High | Rubber/EPDM | High |
| Painted Surface | High | Acrylic/PET | High |
| Wood/Board/Paper | High | Polystyrene | High |
| Soft PVC | Low | PP/PE/PS | High |
| Rigid PVC | High | Smooth substrate | High |
| PC/ABS | High | Rough substrate | High |

RESISTANCE

Resistant to water, detergents and alcohol. Low resistance to plasticizers and low outdoor resistance. Not recommended for use in contact with aliphatic or aromatic hydrocarbons. For further technical advice, please consult with MACtac.

SHELF LIFE

2 years when stored at 15/25°C and 50% relative humidity.

ADHESIVE DATA

| | TYPICAL VALUES (*) | TEST METHOD |
|--|--------------------|-------------|
| Quick Tack (N/25mm) on stainless steel | 28 | FTM 9 |
| Peel 180°- (N/25mm) on stainless steel | | |
| - after 20 minutes | 38 | FTM 1 |
| - after 24 hours | 40 | FTM 1 |
| Shear on stainless steel 1kg-25 mm x 25mm (hours) | > 1000 | FTM 8 |

CARRIER DATA

| | TYPICAL VALUES (*) | TEST METHOD |
|-------------------------|--------------------|-------------|
| Thickness (µ) | 20 | ISO 534 |
| Tensile (N/15mm) (min.) | MD 17 CD 10 | DIN 53455 |
| Elongation (%) (max.) | MD 500 CD 750 | DIN 53455 |

TEMPERATURE RESISTANCE

| | |
|---------------------------------|------------------|
| Minimum application temperature | 5°C |
| End-use temperature range (**) | - 40°C to + 80°C |

(**) when working under extreme T° of this range , please contact Mactac for further information.

RELEASE LINER

| | |
|---------------------------------------|---------|
| Silicone paper white of 60gr/sqm | ISO 536 |
| THICKNESS (Carrier+Adhesive) 100 µ | ISO 534 |

(*) Values given are typical and are not necessarily for use in specifications.

IMPORTANT NOTICE

All MACtac products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning MACtac products are based upon research which the Company believes to be reliable but such information do not constitute a warranty. Because of the variety of possible uses for MACtac products and the continuing development of new uses, the purchaser should carefully consider the fitness and performance of the product for each intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product or for incidental or consequential damages. All specifications are subject to change without prior notice.

